



product
information

6G61-WHE12426
REGLAZING WHITE PRIMER

Cardinal' 6G61-WHE12426 is a 250 g/l VOC two-component polyurethane primer designed to be applied direct to a variety of reglazing substrates. The product is defined by fast dry, chemical resistance, hydrolysis resistance, adhesion and sand ability.

TYPICAL USES:

- Primer coat decorative and protective uses

BENEFITS:

- Low VOC content
- Excellent sand ability
- RoHS / WEEE compliant

REPAIR OR REFINISHING: Clean surface to be repainted, remove dirt, grease, oil, and all other contaminants. Abrade surface if necessary. Tack surface clean.

SURFACE PREPARATION AND PRIMING: The most important steps in a successful coating process are cleaning, pretreatment and priming. The following is a brief outline of some basics for unpainted substrates. It is not intended to be all-inclusive. For more information on your particular application contact Cardinal.

Cleaning the substrate: All surfaces to be coated, must be free of dirt, grease, oil, oxidation, mill scale, and all other contaminants. The surface must be thoroughly dry before painting. Air quality regulations have limited the allowable emissions from cleaning operations.

Steel — A phosphate chemical conversion coating is highly recommended. When this is not possible, apply directly to a clean surface a uniform coat of 4W02-E04626.

Aluminum — A chemical conversion coating is highly recommended. When this is not possible, a vinyl acid wash pretreatment primer is recommended such as Cardinal's 4860 series primers.

Related Products:

PRODUCT NO.	DESCRIPTION
HP-439	Slow Exempt Reducer
SB-32	Slow Reducer

THIS COATING MUST BE USED
ONLY IN A WELL VENTILATED
AREA!
KEEP THIS COATING AWAY
FROM ANY AND ALL SOURCES
OF IGNITION!

TYPE: Acrylic

COMPONENTS: Two.

COLORS: White

GLOSS: Semi-gloss.

COVERAGE: At 1.0 mil DFT.

700 ft²/gal. at 100% transfer efficiency (TE)

450 ft²/gal. at 65% TE

Calculation: 1604 ft²/gal x % volume solids x TE ÷ DFT

VOC: (as supplied)

88 grams/liter = 0.73 lbs/gal less water

42 grams/liter = 0.35 lbs/gal including water

VOLUME SOLIDS: 44%

FLASH POINT: -4°F TCC

SHELF LIFE: 1 year from date of manufacture in factory sealed container.

Mix Ratio:

Component	Parts by Volume
6G61-WHE12426	9
6GHP	1
SB-32 REDUCER	3

APPLICATION: Thoroughly stir or agitate paint before applying. This material is designed for spray application. Brushing, rolling and dipping are not recommended. See surface preparation and priming section for further instructions.

RECOMMENDED SPRAY EQUIPMENT:

HVLP; fluid nozzle 97, air cap 93P, fluid pressure 40-50 psi, air pressure 55psi

VISCOSITY: 30" – 40" seconds, #3 Zahn cup at 78°F.

RECOMMENDED DFT: 1.0 – 2.0 mils

CURE:

DRYING TIME:	Set-to-Touch	Dry-to-Handle	Full Cure	Recoat
Air Dry				
Substrate temperature 68F	2 hours	6 hours	7 days	3 hours

Note: Adhesion needs to be tested prior to use!

(Continued on page 2)

So. El Monte, CA 1329 Potrero Ave. 91733 (323) 283-9335 (626) 444-9274 Fax (626) 444-0382

www.cardinalpaint.com

NO WARRANTY EXPRESSED OR IMPLIED, ACCEPTABILITY TO BE DETERMINED BY USER, SPECIFICATIONS ARE SUBJECT TO CHANGE WITHOUT NOTICE

Trouble Shooting:

PROBLEM	CAUSE	REMEDY
Too thin / low viscosity	Over reduced.	Remix at correct ratio
Dry spray	High atmospheric temperature. Over atomization Gun to part distance	Increase fluid pressure & decrease atomizing pressure. Reduce with SB-17: 1% - 2%. Add SB-17 at rate of 1 oz./gal.
Craters	Contamination of substrate, application equipment or environment.	Find and eliminate source of contamination. When craters persist, add ½ oz./gal of 6SLA-100 additive.
Poor adhesion	Improper surface preparation.	See surface preparation section.

EQUIPMENT CLEAN-UP: 1000-13 should always be used for primary cleaning. If something different is needed exempt solvents can be used for secondary cleaning, air quality regulations, in your area may have limited the allowable emissions from cleaning operations.

Product Limitations:

- Storage stability is limited to 6 months.

SAFETY: Refer to the product's Material Safety Data Sheet (MSDS) for complete safety information.

Contains organic solvents. Use with adequate ventilation. Do not breathe vapors or spray mists. If component TLVs are exceeded, a NIOSH approved air supplied respirator is advised. See MSDS for TLV information.

Contents are FLAMMABLE. Keep from heat, sparks or open flame.

Allergic reactions are possible. Avoid use by persons with respiratory problems.


Avoid contact with eyes, skin, and clothing. Wash thoroughly after handling.

FIRST AID:

Eye contact: flush immediately with plenty of water for at least 15 min. and get medical attention.


Skin contact: wash thoroughly with soap and water for 5 minutes.

If swallowed, do not induce vomiting, get medical attention immediately.



PRODUCT IDENTIFICATION

6 G 6 1 – WHE 1 2 4 2 6 (example)



G12TL